



SUNVIS 800 HYDRAULIC OILS

OVERVIEW

SUNOCO SUNVIS 800 HYDRAULIC OILS are highly refined, premium quality, anti-wear hydraulic oils recommended for use in a wide range of applications. Designed for use in piston, gear pumps, and vane pumps used in industrial and mobile hydraulic systems, SUNOCO SUNVIS 800 HYDRAULIC OILS provide exceptional wear protection for pumps, motors, and other hydraulic system components. All grades have very good oxidation resistance, rust and corrosion protection and foam resistance to provide long service with minimal upkeep.

FEATURES & BENEFITS

SUNOCO SUNVIS 800 HYDRAULIC OILS utilize highly refined base stocks for long service life, robust anti-wear technology for exceptional protection and resistance to oxidation, rust, corrosion, and foaming and offer superior component protection and smooth power transmission. SUNOCO SUNVIS 832-868 hydraulic oils also offer a high dielectric strength for applications requiring an electrical insulating fluid.*

*Dielectric strength measurement given at point of manufacture. Dielectric strength deteriorates rapidly with contamination from particulates and moisture; oil must be kept clean and dry at all times

APPLICATIONS

SUNOCO SUNVIS 800 HYDRAULIC OILS are designed for a variety of applications including hydraulic systems, mining equipment, and moderately loaded gear sets, as well as for general purpose lubrication.

SPECIFICATIONS

AFNOR NF E 48-603 (HM) , NF E 48-690, NF E 48-691 • AIST 126 (US Steel) • AIST 127 (US Steel) • ANSI/AGMA 9005-E02-RO • ASLE 64-1 to 64-4, 70-1 to 70-3 • ASTM D6158 (HM, HV) • Bosch Rexroth RDE 90235 • CETOP RP91H • Cincinnati Machine P-68, P-69 & P-70 (• DIN 51524-2 (HM) & 51524-3 (HV) • Eaton I-286-S3 (Industrial equipment) • Eaton M-2950-S (35VQ25 pump test) • GMLS-2 • ISO 11158 (HM, HV) • ISO 20763 Conestoga vane pump test • JCMAS P041 HK Hydraulic Specification • Parker (Denison) HF-0, HF-1 & HF-2 (T6H20C pump testing) • SAE MS1004 (HM, HV) • SEB 181222

TYPICAL PROPERTIES

| | 4203 | 4333 | 4343 | 4383 | 4493 | 4803 |
|-------------------------|------------|------------|------------|------------|-------------|-------------|
| Product Code | 4203 | 4333 | 4343 | 4383 | 4493 | 4803 |
| Product | Sunvis 810 | Sunvis 832 | Sunvis 846 | Sunvis 868 | Sunvis 8100 | Sunvis 8150 |
| Viscosity, cSt @ 40 °C | 10 | 32 | 46 | 68 | 100 | 150 |
| Viscosity, cSt @ 100 °C | 2.7 | 5.4 | 6.9 | 8.9 | 11.4 | 14.6 |
| Viscosity Index | 105 | 100 | 100 | 100 | 98 | 96 |
| Flash Point, °F | 400 | 405 | 410 | 453 | 415 | 470 |
| Pour Point, °C | -40 | -38 | -37 | -34 | -32 | -15 |
| Zinc, wt% | .043 | .043 | .043 | .043 | .043 | .043 |
| Oxidation Stability | 5000+ | 5000+ | 5000+ | 5000+ | 4000+ | 3000+ |
| Demulsibility | 20 | 20 | 20 | 20 | 20 | 20 |
| Copper Corrosion | 1b | 1b | 1b | 1b | 1b | 1b |
| Rust Test | Pass | Pass | Pass | Pass | Pass | Pass |
| FZG Pass, Load Test | 10 | 10 | 10 | 10 | 10 | 10 |
| Color, max | 1.5 | 1.5 | 1.5 | 1.5 | 2.5 | 2.5 |